



POWEROIL TO 1020 AUT

POWEROIL TO 1020 AUT is a Trace Inhibited Transformer Oil meeting the ASTM D 3487 - 2006 Type I Standard Specification. It also meets the ASTM D 1275 B Test requirement for Corrosive Sulphur.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Visual Examination		Simple visual examination of the oil sample	Clear and bright	
2	Aniline Point	° C	ASTM D 611	63	84
3	Colour		ASTM D 1500		0.5
4	Specific Gravity 15 ° C / 15 ° C		ASTM D 1298		0.91
5	Kinematic Viscosity at 100 ° C	cSt (SUS)	ASTM D 445 or D 88		3.0 (36)
	at 40 ° C				12.0 (66)
	at 0 ° C				76 (350)
6	Flash Point, COC	° C	ASTM D 92	145	
7	Pour Point	° C	ASTM D 97		- 40
8	Inter Facial Tension at 25 ° C	dynes / cm	ASTM D 971	40	
9	Neutralization Number, Total Acid Number	mg KOH/ gm	ASTM D 974		0.03
10	Water Content	ppm	ASTM D 1533		35
11	Breakdown Voltage at 60 Hz Disc electrode	kV	ASTM D 877	30	
12	Breakdown Voltage Impulse conditions 25 ° C , needle negative to sphere grounded, 1- in (25.4 mm) gap	kV	ASTM D 3300	145	
13	Dielectric Dissipation Factor (Tan δ) at 60 Hz at 25 ° C at 100 ° C		ASTM D 924		0.05 0.30
14	Corrosive Sulphur Copper Strip, 140 ° C, 19 Hrs Copper Strip , 150 ° C, 48 Hrs		ASTM D 1275 A ASTM D 1275 B	Non Corrosive Non Corrosive	
15	Oxidation Inhibitor Content	%	ASTM D 1473 or D 2668		0.08
16	Oxidation Stability at 110 ° C, 72 Hrs		ASTM D 2440		
	Total Acid Number	mg KOH /gm			0.5
	Sludge	%			0.15
	at 110 ° C , 164 Hrs				
	Total Acid Number	mg KOH /gm			0.6
	Sludge	%			0.3
17	Gassing Tendency at 80 ° C Procedure B Test Voltage 10 kV	µ L / min	ASTM D 2300 by Procedure B		+ 30
18	PCB Content	ppm	ASTM D 4059	Not Detectable	

(Version # 3 October 31st , 2007)

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.