

POWEROIL TO 335 HX

POWEROIL TO 335 HX is a High Grade Inhibited Transformer Oil with higher oxidation stability and lower Sulphur content meeting Type II of IS 335:2018 (Fifth Revision) Standard – Specific Requirements for Special Applications Specification.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Appearance		Visual inspection of oil sample in transmitted light under a thickness of 10 cm at ambient temperature	Clear free from sediment and suspended matter	
2	Density at 20 ° C	g /ml	IS 1448 (Part 16)		0.895
3	Kinematic Viscosity at 40 ° C	mm ² / sec	IS 1448 (Part 25)		15
	at 0 ° C		IS 1448 (Part 25)		1800
4	Flash Point, PMCC	° C	IS 1448 (Part 21)	135	
5	Pour Point	° C	IS 1448 (Part 10/Sec 2)		- 10
6	Inter Facial Tension at 25 ° C	mN / m	ASTM D 971	No General Requirement 40 min	
7	Acidity	mg KOH/ g	IEC 62021-1		0.01
8	Water Content, Bulk/ Drum, IBC	mg / kg	IEC 60814		30 / 40
9	Breakdown Voltage		IS 6792		
	As Delivered / After Treatment	kV		30 / 70	
10	Dielectric Dissipation Factor (Tan δ) at 90 ° C & 40 to 60 Hz		IS 16086		0.005
11	Corrosive Sulphur Silver Strip, 100 ° C, 18 Hrs.		DIN 51353	Not Corrosive	
12	Potentially Corrosive Sulphur		IS 16310	Not Corrosive	
13	DBDS	mg / kg	IS 16497 (Part 1)	Not Detectable (< 5 mg/kg)	
14	Total Sulphur Content	%	ISO 14596 / ASTM D 4294	No General Requirement	
15	Inhibitors content	%	IS 13631 / IEC 60666	(I) Inhibited Oil (0.08 % to 0.40 %)	
16	Metal Passivator additives	mg / kg	IS 13631 / IEC 60666	Not Detectable (< 5 mg/kg)	
17	Other Additives			Does not contain any additives other than antioxidant additive	
18	Oxidation Stability at 120 ° C, 500 Hrs.		IS 12422		
	Total Acidity	mg KOH /g	4.8.4 of IS 12422		0.3
	Sludge	%	4.8.1 of IS 12422		0.05
	DDF at 90 ° C		4.8.5 of IS 12422		0.05
19	Gassing Tendency	µ L / min	IEC 60628 , Method A	No General Requirement	
20	PCA Content	%	IP 346		3
21	PCB Content	mg / kg	IS 16082	Not Detectable (< 2mg /kg)	
22	2 – Furfural and related compounds content	mg / kg	IS 15668	Not Detectable (< 0.05 mg/kg) for each individual compound	
23	ECT		See 6.14 of IS 335:2018	No General Requirement	
24	Particle Content		IS 13236	No General Requirement	